



PRODUCT NAME

14 Line Polyurethane

ISSUE DATE 27/09/2006

PRODUCT CODE TOP14

VERSION 1.0

VERSION DATE 27/09/2006



PRODUCT DESCRIPTION

A high build, high solids Polyurethane based on a unique blend of Polyurethane Alkyds.

It combines a long wet edge time with excellent hot spray application offering superb durability and gloss retention.

14 Line Polyurethane may also be brushed directly from the can or with the addition of a small amount of Thinner.

14 Line is also suitable for use on concrete flooring (consult technical regarding other types of flooring).



IMPORTANT INSTRUCTIONS BEFORE USE

- Read and follow MSDS, TDS and label instructions
- Stir all paints thoroughly before use
- Always use the same batch number on the same job
- Check colour & sheen. Paintman Paint will not accept any discrepancies arising after use
- Filter the product immediately before use
- Reduce emissions and maintain quality by replacing tin lid after use
- If in any doubt speak Paintman Paint Technical Service Department on 01777 710100



SPECIAL PROPERTIES

- Properties can be enhanced by the addition of Hardener 9029 (ZIP). Use 10 parts Base to 1 part Hardener.



MAXIMUM VOC CONTENT (RFU)

0.416 Kg/L

REGULATIONS / COMPLIANCE

2004/42 IIB (D) 420



COLOUR RANGE

Available in a wide colour range including Fleet, RAL & BS shades



GENERAL INFORMATION

COVERAGE	10 square metres per litre @ 55 microns dft
FLASHPOINT	>30°C
STORAGE	Store between 5°C - 25°C. When not in use, cans must be kept sealed
SHELF LIFE	12 months from delivery date in original sealed containers



ADDITIONAL TECHNICAL INFORMATION

For hot spray application, heat to a maximum of 70°C.



CLEANING

Ensure surfaces to be coated are dry and must be cleaned using the appropriate Paintman Paint product to remove all traces of contaminants.

Paintman Paint produce a full range of cleaners, silicone removers, degreasers and preparatory cleaners suitable for the cleaning process.

Please refer to our website for Method of Use Articles for Prep-Cleaning Techniques and Preparatory Cleaners from the Product Guide



SURFACE PREPARATION

Please refer to Method of Use Articles for details on Surface Preparation.



SUITABLE SUBSTRATE & THEIR SUITABLE PREPARATION

MILD STEEL

Remove millscale and thoroughly degrease using suitable Paintman Paint Prep Clean
Abrade with P80-P180 if necessary before applying Paintman Paint Primer

SHOT BLASTED STEEL

Remove all traces of blast grit/sand before applying Paintman Paint Primer

GRP

Abrade with P180-P320

Degrease using suitable HMG Prep Clean before applying Paintman Paint Primer

ALUMINIUM

Abrade with P180-P320

Degrease with suitable Paintman Paint Prep Clean

Coat with appropriate Paintman Paint Etch Primer, and if required Paintman Paint Primer

GALVANISED STEEL

Abrade with P180-P320

Degrease with suitable Paintman Paint Prep Clean

Apply Paintman Paint Mordant Wash

Coat with appropriate Paintman Paint Etch Primer, and if required Paintman Paint Primer



SUGGESTED PRIMER / FILLER / SEALER SYSTEMS

Synthetic BDX Primer

Synthetic High Opacity Undercoat

Speedbuild 3 Primer





HEALTH AND SAFETY

Refer to SDS and tin label prior to use.

Suitable respiratory equipment should be worn when spraying

Contaminated Rags, Spray Booth Filters or other substrates should be segregated from other chemical waste, soaked with Water and disposed of in a non-combustible container with a tight fitting Lid.



APPLICATION METHODS

COMPLIANT SPRAY GUN		PRESSURE POT		AIRLESS/AIR-ASSISTED		HOT SPRAY	
MIXING RATIO							
Base Thinner	5 Up to 1	Base Thinner	5 Up to 1	Base Thinner	5 Up to 1	Base Thinner	5 Up to 1
THINNER OPTIONS							
Thinner 2612 Thinner 2611		Thinner 2612 Thinner 2611		Thinner 2612 Thinner 2611			
VISCOSITY							
30-35	Seconds B4 cup	30-35	Seconds B4 cup	30-35	Seconds B4 cup	30-35	Seconds B4 cup
SPRAY GUN SETUP							
1.6-1.8		1.2-1.4		11-13 thou 40/50°		1.6-1.8	
FLASH OFF							
20 mins between coats		20 mins between coats					
NUMBER OF COATS (GUIDE ONLY)							
1 Light + 1 full coat		1 Light + 1 full coat		1 full coat		1 full coat	
DRYING TIME							
Touch dry Hard dry	2hrs @20°C 8hrs @20°C	Touch dry Hard dry	2hrs @20°C 8hrs @20°C	Touch dry Hard dry	2hrs @20°C 8hrs @20°C	Touch dry Hard dry	2hrs @20°C 8hrs @20°C
RECOATABILITY / OVERCOATING							
Min 24hrs depending on build & temp. Surface should be de-nibbed prior to overcoating							
WET FILM THICKNESS*							
100 microns		100 microns		100 microns		100 microns	



Paintman Paint Ltd, Unit 7
Trinity Park Industrial Estate, Sloswicke Drive,
Retford, DN22 7XG
Tel: 01777 710100
sales@paintman.co.uk / www.paintman.co.uk



DRY FILM THICKNESS*

55 microns	55 microns	55 microns	55 microns
------------	------------	------------	------------

** - Paintman Paint Technical Data Sheets indicate a Dry Film Thickness that will be achieved when applying a particular Wet Film Thickness. These values are a guide only and are not to be used as specifications. Film thickness will vary depending on actual use and specification. Great care should be taken to achieve the dft stated in the agreed specification and to avoid areas of excessively low or high thickness.*

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of Paintman Paint's knowledge and belief accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. For professional use only.