

PRODUCT NAME

A1242 Undercoat

ISSUE DATE 22/09/2005 PRODUCT CODE PRIA1242 VERSION 1.0 VERSION DATE 22/09/2005



PRODUCT DESCRIPTION

A 1K alkyd / polyurethane undercoat with superior brushing qualities and excellent obliteration properties.

This product is especially suitable for large areas due to its ease of application and long wet edge time.



IMPORTANT INSTRUCTIONS BEFORE USE

- Read and follow MSDS, TDS and label instructions
- Stir all paints thoroughly before use
- Always use the same batch number on the same job
- Check colour & sheen. Paintman Paint will not accept any discrepancies arising after use
- Filter the product immediately before use
- Reduce emissions and maintain quality by replacing tin lid after use
- If in any doubt speak Paintman Paint Technical Service Department on 01777 710100



MAXIMUM VOC CONTENT (RFU)

0.400 Kg/L REGULATIONS / COMPLIANCE

2004/42 IIB (C) 540



COLOUR RANGE

White & Cream

COVERAGE

STORAGE

SHELF LIFE

FLASHPOINT

TEMP RESISTANCE



GENERAL INFORMATION

12 square metres per litre @ 55 microns dft 37°C 80°C Store between 5°C - 25°C. When not in use, cans must be kept sealed 12 months from delivery date in original sealed containers



CLEANING

Ensure surfaces to be coated are dry and must be cleaned using the appropriate Paintman Paint product to remove all traces of contaminants.

Paintman Paint produce a full range of cleaners, silicone removers, degreasers and preparatory cleaners suitable for the cleaning process.

Please refer to our website for Method of Use Articles for Prep-Cleaning Techniques and Preparatory Cleaners from the Product Guide



SURFACE PREPARATION

Please refer to Method of Use Articles for details on Surface Preparation.



HEALTH AND SAFETY

Refer to Health & Safety Data Sheet prior to use. Suitable respiratory equipment should be worn when spraying



			AF	PLICATION M	ETHODS		
	E	BRUSH	COMPLIAN	IT SPRAY GUN			
	MIXING RAT Base	IO rfu	Base Thinner	10 1			
	THINNER OPTIONS Thinner 2612		Thinner 2612	2			
s	VISCOSITY		25-35 Secs	Seconds DIN4			
Ì	SPRAY GUN	SETUP	1.8				
	NUMBER OF COATS (GUIDE (2 coats		ONLY) 2 Full Coats				
	FLASH OFF		15 mins betw	15 mins between coats			
N F	DRYING TIM Touch dry Hard dry	E 3hrs @20°C 16hrs @20°C	Touch dry Hard dry	3hrs @20°C 16hrs @20°C			
	WET FILM THICKNESS* 100 microns DRY FILM THICKNESS* 55 microns		100 microns				
			55 microns				

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of Paintman Paint's knowledge and belief accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to it's accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. For professional use only.